

M SEALS PKFG30-CRD89

Glass Fibre Filled PEEK

MATERIAL DATA SHEET (Version 6.0 – 05.2022)



Description

M Seals PKFG30-CRD89 material is a high-performance glass fibre reinforced PEEK material. This material has excellent thermal resistance, high compressive strength, low wear properties and low creep values.

PKFG30-CRD89 material is commonly used for guide rings, back-up rings, wear rings, bushes, valve seat seals, scraper seals and other applications requiring excellent compressive strength together with hydrolysis and steam resistance.

Physical Properties

Property	Test method	Unit	Typical value	
Type			SM	EX
Colour			Beige	Beige
Density	ISO 1183	g/cm ³	1.53	1.51
Hardness	ISO 868	Shore D	89	89
Tensile Strength	ISO 527-2	MPa	107	80
Tensile strength at yield	ISO 527-2	MPa	107	80
Elongation at break	ISO 527-2	%	2.1	5
Modulus of elasticity	ISO 527-2	Mpa	7230	6000
Glass transition temperature *	DIN 53765	°C	+147	-
Melting temperature	DIN 53765	°C	+341	+343
Service temperature short term **		°C	+300	+300
Service temperature long term **		°C	-20/+260	-20/+250

* (Information found from public sources)

** (Individual testing in application conditions is mandatory)

SM= Special manufacturing technique

EX= Extruded manufacturing technique

Main Characteristics

- Excellent thermal resistance
- High compressive strength
- Good sliding ability
- Good creep resistance
- Good wear properties
- Hydrolysis & steam resistance

Typical products

- Wear strip
- Bearing rings / guide rings
- Bushes
- Valve seat seals
- Anti-Extrusion / Back-Up Rings
- Bespoke parts

Typical Applications

Due to its excellent thermal resistance, compressive strength and sliding ability, this material is an excellent material choice for back-up ring and wear ring applications where standard PEEK materials may not be suitable or where higher compressive strength is required. PKFG30-CRD89 is commonly used within the Oil and Gas and Aerospace industries.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales.esd@m-seals.co.uk . Web: www.m-seals.com

M Seals believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however M Seals makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.