

# M SEALS SIL-BL85

Blue FDA compliant Silicone Elastomer Material

MATERIAL DATA SHEET (Version 6.0 – 05.2022)



FDA compliant



EC1935-2004 compliant



ADI free

## Description

SIL-BL85 is an 85a Shore FDA compliant Silicone elastomer material which has been migration tested to comply with FDA requirements CFR 21 177.2600 for food contact use. Silicone elastomers exhibit excellent chemical and thermal resistance against a wide range of media and those commonly found within the food industry.

We do not recommend the use of Silicone elastomers in dynamic applications due to their poor abrasion resistance.

## Physical Properties

Property	Test method	Unit	Typical value
Colour			Red
Density	ISO 1183-1	g/cm <sup>3</sup>	1.54
Hardness	ISO 7619-1	Shore A	85 (+/-5)
Tensile Strength	DIN 53504	MPa	7.5
100% Modulus	DIN 53504	MPa	6.1
Elongation at break	DIN 53504	%	117
Compression set (24 Hours @ 100°C, 25%)	ISO 815-1	%	4.8
Compression set (24 Hours @ 175°C, 25%)	ISO 815-1	%	10.8
Minimum service temperature		°C	-55
Maximum service temperature		°C	+180

### Global migration results of FDA extraction on SIL-BL85 material samples (mg/inch<sup>2</sup>)

FDA test method	Reflux test conditions	Mean	Limit*	Conclusion
CFR 177.2600 (e)	De-ionised water, 7 hours	<1	20	PASS
CFR 177.2600 (e)	De-ionised water, 2 hours	<1	1	PASS
CFR 177.2600 (f)	N-hexane, 7 hours	17	175	PASS
CFR 177.2600 (f)	N-hexane, 2 hours	<1	4	PASS

## Main Characteristics

- CFR 177.2600 FDA Compliant
- Extraction tested and passed
- No tooling required
- ADI free
- Blue in colour

## Typical Products

- Triclover seals
- RJT seals
- DIN 11851 D-Seals
- Butterfly valve seals
- Static seals / O-Rings

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: [sales.esd@m-seals.co.uk](mailto:sales.esd@m-seals.co.uk) . Web: [www.m-seals.com](http://www.m-seals.com)

M Seals believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however M Seals makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.