


M SEALS PTG15-WD60

Glass Fibre Filled PTFE


MATERIAL DATA SHEET (Version 6.0 – 05.2022)



High Temperature



Chemical resistance



Low Friction

Description

M Seals PTG15-WD60 material is a modified PTFE which has been reinforced with a filler of 15% glass fibre by weight. The addition of glass fibre fillers to PTFE provides higher compressive strength, lower wear properties and lower creep values.

Glass filled PTFE material is commonly used for composite seals, valve seat seals, guide rings, wear rings and bushes. It is highly chemical resistant except for strong alkalis and hydrofluoric acid (HF).

Physical Properties

Property	Test method	Unit	Typical value
Colour			White/Cream
Density	ASTM D792	g/cm ³	2.19 - 2.22
Hardness	ASTM D2240	Shore D	≥58
Tensile Strength	ISO 527	N/mm ²	≥17
Elongation at break	ISO 527	%	≥250
Compressive strength at 1% deformation	ASTM D695	N/mm ²	6 - 7
Deformation under load *	ASTM D621	%	≤14
Permanent deformation **	ASTM D621	%	≤7
Coefficient of Linear Thermal Expansion ***	ASTM D696	10 ⁻⁵ (mm/mm)/ °C	11 - 13
Dynamic coefficient of friction	ASTM D3702	Points	0.12
Service temperature ****		°C	-200 to +260

* (24 Hours @ 13.7 N/mm² @ 23°C)

** (After 24h relaxation)

*** (+25 to +100°C)

**** (Individual testing in application conditions is mandatory)

Main Characteristics

- Good compressive strength
- Good sliding ability
- Good dimensional stability
- Low creep rate
- Good wear properties

Typical Products

- Composite seals
- Wear strip
- Bearing rings / guide rings
- Bushes
- Valve seat seals

Typical Applications

Due to its good dimensional stability, compressive strength and sliding ability, PTG15-WD60 is an excellent material choice for composite seals, valve seat seals, guide rings, wear rings, slideways and bearing bushes. As mentioned above, it should not be used in strong alkalis or hydrofluoric acid (HF).

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales.esd@m-seals.co.uk . Web: www.m-seals.com

M Seals believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however M Seals makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.