

M SEALS ZC200

High Temperature & Hot Water / Steam Resistant FFKM
(Perfluoroelastomer)

M SEALS
- Part of Diploma PLC

MATERIAL DATA SHEET (Version 6.0 – 05.2022)



High Service Temperature

Description

This FFKM compound has been developed to meet severe service requirements where application conditions may involve high temperature use and/or sealing of water and steam. The compound has similar chemical resistance to that of PTFE while providing elastomeric properties comparable to more standard Fluorocarbon rubbers.

ZC200 provides excellent temperature resistance up to +300°C and is a good choice for applications where other elastomers are not suitable.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Black
Hardness	ISO 48	IRHD	78
Tensile Strength	ISO 37	MPa	21.2
Modulus @ 100%	ISO 37	MPa	12.9
Elongation at break	ISO 37	%	165
Tear Strength	ISO 34	N/mm	25.1
Specific Gravity	ISO 2781	g/cm ³	2.00
Compression Set Value in Air (24 Hours @ 204°C – 25% Strain)	ISO 815		15.3
Minimum service temperature		°C	-15
Maximum service temperature		°C	+300

Main Characteristics

- Developed for high temperature water and steam
- Superb thermal resistance
- Broad chemical resistance similar to PTFE
- Good compression set resistance
- Excellent performance in harsh conditions

Typical Products

- O-Ring Seals
- X-Ring Seals
- Piston T-Seals
- Rod T-Seals
- Custom parts

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales.esd@m-seals.co.uk . Web: www.m-seals.com

M Seals believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however M Seals makes no warranty, expressed or implied, that parts manufactured from this / and/or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.