

M SEALS SIL-C79

Clear / Translucent Soft Grade FDA compliant Silicone



MATERIAL DATA SHEET (Version 6.0 – 05.2022)



FDA compliant
EC 1935/2004 compliant



ADI free

Description

SIL-C79 is a clear / translucent 79a Shore soft grade FDA compliant Silicone elastomer material. The material components used for development of this material are in accordance with FDA CFR 177.2600 and EC 1935/2004 regulations and are allowed for repeated food contact use.

Silicone elastomers exhibit excellent chemical and thermal resistance against a wide range of media and those commonly found within the food industry.

We do not recommend the use of Silicone elastomers in dynamic applications due to their poor wear and abrasion resistance.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Clear
Density	ISO 1183-1	g/cm ³	1.18
Hardness	DIN 53505	Shore A	79 (+/-5)
Tensile Strength	DIN 53504	MPa	>8.9
Elongation at break	DIN 53504	%	>320
Tear strength	ISO 34-1	N/mm	>18
Rebound resilience	DIN 53512	%	38
Compression set (24 Hours @ 170°C, 25%)	ISO 815-1	%	<20
Minimum service temperature		°C	-50
Maximum service temperature		°C	+210
Maximum service temperature (Hot water / Steam)		°C	+110

Main Characteristics

- FDA & EC 1935/2004 ingredient compliant
- Clear / Translucent colouring
- Soft Grade
- ADI free
- Excellent chemical resistance

Typical Products

- Triclover seals
- RJT seals
- DIN 11851 D-Seals
- Butterfly valve seals
- Static seals / O-Rings