

M SEALS PTE10-CRD57

Polymer Reinforced PTFE

MATERIAL DATA SHEET (Version 6.0 – 05.2022)




- Part of Diploma PLC



High Temperature



Chemical Resistance



Low Friction



Wear Resistance



FDA Compliant

Description

M Seals PTE10-CRD57 is a proprietary polymer reinforced PTFE that has outstanding wear and temperature resistance and does not wear metallic surfaces, it is commonly referred to as Ekonol® filled PTFE.

PTE10-CRD57 resists self-wear better than most other filled PTFE materials, it has good chemical resistance, self-lubricating properties, very low thermal expansion and FDA compliance making it a unique filled grade of PTFE.

PTE10-CRD57 is recommended for use with soft (un-hardened) metals and applications involving gases, high temperature or where its FDA compliance is required. It should **not** be used in any applications where steam, concentrated Sulphuric acid and strong Alkalies are present.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Beige
Density	ASTM D792	g/cm ³	1.96 – 2.06
Hardness	ASTM D2240	Shore D	>55
Tensile Strength	ISO 527	N/mm ²	>14
Elongation at break	ISO 527	%	>220
Deformation under load *	ASTM D621	%	<13
Permanent deformation **	ASTM D621	%	<8
Coefficient of Linear Thermal Expansion ***	ASTM D696	10-5 (mm/mm)/ °C	8 - 10
Dynamic coefficient of friction	ASTM D3702	Points	0.13
Service temperature ****		°C	-200 to +260

* (24 Hours @ 13.7 N/mm² @ 23°C)

** (After 24h relaxation)

*** (+25 to +100°C)

**** (Individual testing in application conditions is mandatory)

Ekonol® is a registered trademark of SOHIO Co

Main Characteristics

- Good compressive strength
- Good sliding ability
- Lower creep rate compared to unfilled / Virgin PTFE
- Good wear properties
- Does not abrade surfaces

Typical Products

- Spring energised seals
- Wear strip
- Bearing rings / guide rings
- Bushes
- Valve seat seals

Typical Applications

PTE10-CRD57's unique anti wear properties make it an excellent material choice for rotary seals or high frequency dynamic applications working on soft / un-hardened metals.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales.esd@m-seals.co.uk . Web: www.m-seals.com

M Seals believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however M Seals makes no warranty, expressed or implied, that parts manufactured from this / and/or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.